

MITSUBISHI CEMENT CORPORATION

CERTIFICATE OF TEST

Source: Cushenbury Plant Limestone Modified Portland Cement - Block Date: 6/9/2017

ASTM designation: C 1157 – 11 for Type HE. Production Period

UBC Standard: Section 21.303.1 Vol. 3 From: 5/12/2017

To: 5/19/2017

Chemical Composition:	ASTM Limits	UBC Limits	Test Results
Silicon Dioxide (SiO ₂), %			19.6
Aluminum Oxide (Al ₂ O ₃), %			4.7
Ferric Oxide (Fe ₂ O ₃), %			1.1
Calcium Oxide (CaO), %			64.4
Magnesium Oxide (MgO), %			1.9
Sulfur Trioxide (SO ₃), %			2.9
Loss on Ignition, %		7.0 Max.	5.7
Insoluble Residue, %		1.5 Max.	0.7
Total Alkali (%Na ₂ O + 0.658 * %K ₂ O), %			0.39
Tricalcium Silicate (C ₃ S), [b] %			50
Tricalcium Aluminate (C ₃ A), [b] %			11
CO ₂ , %			5.0
Limestone, %	15 Max.		12.2
Limestone Purity, %		85 Min.	93
Free Lime, %			1.1
PHYSICAL RESULTS:			
Blaine Fineness Average (m²/kg)			553
325 Mesh (% Passing)			98.3
Autoclave Expansion (%)	0.80 Max.		0.06
Mortar Bar Expansion (%) April 2017	0.020 Max.		0.004
Time of Set Initial Vicat (minutes)	45 / 420 Min. /	Max	92
Air Content (% by Volume)	12 Max	22 Max.	6.7
Heat of Hydration (kJ/kg)	(a)		379
Color (L value)	(a)		78
Compressive Strength Test:	ASTM Limits MPA psi		MPA PSI
1 Day		Min.	21.3 3083
3 Day		Min.	32.2 4663
7 Day	27.0 J700 I	·	36.5 5293
28 Day April 2017			42.2 6117

This cement has been sampled and tested in accordance with ASTM standard methods and procedures. All tests results are certified to comply with the type specification designated above. No other warranty is made or implied. We are not responsible for improper use or workmanship. [a] For information only. [b] Adjusted per ASTM C150 A1.6

MITSUBISHI CEMENT CORPORATION
Cushenbury plant

Tom Gepford Quality Control Manager



MITSUBISHI CEMENT CORPORATION

CERTIFICATE OF TEST

Source: Cushenbury Plant Limestone Modified Portland Cement - Block Date: 6/9/2017

ASTM designation: C 1157 – 11 for Type HE. Production Period

UBC Standard: Section 21.303.1 Vol. 3 From: 5/12/2017

To: 5/19/2017

Additional Data

Limestone Addition

% Addition:	12.2
SiO2 (%)	3.2
Al_2O_3 (%)	1.1
Fe_2O_3 (%)	0.3
CaO (%)	51.4
SO ₃ (%)	0.5

Base Cement Phase Composition

C_3S	56
C_2S	17
C_3A	12
C_4AF	3

We certify that the above described data represents the material used in the cement manufactured during the production period indicated.

MITSUBISHI CEMENT CORPORATION
Cushenbury plant

Tom Gepford Quality Control Manager