



# MITSUBISHI CEMENT CORPORATION

## CERTIFICATE OF TEST

Source: Cushenbury Plant

Plastic (Stucco) Cement

Date: 12/13/2012

ASTM designation: C 91 - 05 for Masonry Cement – Type M	Production Period
ASTM designation: C 1328 - 05 for Plastic (Stucco) Cement – Type M	From: 11/1/2012
UBC Standard: 21 - 11 for Cement, Masonry – Type M	To: 11/3/2012
UBC Standard: 25 – 1 for Plastic Cement	

### Chemical Composition:

	Test Results
Silicon Dioxide (SiO <sub>2</sub> ), %	19.4
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	3.6
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	3.4
Calcium Oxide (CaO), %	61.7
Magnesium Oxide (MgO), %	2.3
Sulfur Trioxide (SO <sub>3</sub> ), %	2.3
Loss on Ignition (LOI), %	6.4
Insoluble Residue	0.64
Total Alkali (%Na <sub>2</sub> O + 0.658 * %K <sub>2</sub> O)	0.37
Tricalcium Silicate (C <sub>3</sub> S), %	75
Tricalcium Aluminate (C <sub>3</sub> A), %	3.6
CO <sub>2</sub> , %	5.9
Limestone, %	15.8
CaCO <sub>3</sub> Limestone Purity, %	93

### PHYSICAL RESULTS:

	ASTM C-91 & C-1328 Limits	Test Results
Blaine Fineness (m <sup>2</sup> /kg)		526
325 Mesh (% Passing)	76 Min.	98.5
Autoclave Expansion (%)	1.0 Max.	0.07
Time of Set Initial Vicat (minutes)	90 Min. / 1000 Max.	170
Air Entrainment (% Volume)	8 Min. / 19 Max.	15.0
Water Retention, % of Original Flow	70 Min.	81

### Compressive Strength Test:

	ASTM C-91 & C-1328 Limits	MPA	PSI
	MPA psi		
1 Day		10.0	1445
3 Day		17.8	2575
7 Day	12.4 1800 Min.	24.2	3515
28 Day	20.0 2900 Min.	26.5	3840

This cement has been sampled and tested in accordance with ASTM standard methods and procedures. All tests results are certified to comply with the type specification designated above. No other warranty is made or implied. We are not responsible for improper use or workmanship.

MITSUBISHI CEMENT CORPORATION  
Cushenbury plant

Tom Gepford  
Quality Control Manager



**MITSUBISHI CEMENT CORPORATION**  
**CERTIFICATE OF TEST**

Source: Cushenbury Plant

Plastic (Stucco) Cement

Date: 12/13/2012

ASTM designation: C 91 - 05 for Masonry Cement – Type M

Production Period

ASTM designation: C 1328 - 05 for Plastic (Stucco) Cement – Type M

From: 11/1/2012

UBC Standard: 21 - 11 for Cement, Masonry – Type M

To: 11/3/2012

UBC Standard: 25 – 1 for Plastic Cement

**Additional Data**

**Limestone Addition**

% Addition:	15.8
SiO <sub>2</sub> (%)	3.5
Al <sub>2</sub> O <sub>3</sub> (%)	1.1
Fe <sub>2</sub> O <sub>3</sub> (%)	0.3
CaO (%)	50.4
SO <sub>3</sub> (%)	0.3

**Base Cement Phase Composition**

C <sub>3</sub> S	56
C <sub>2</sub> S	19
C <sub>3</sub> A	4
C <sub>4</sub> AF	12

We certify that the above described data represents the material used in the cement manufactured during the production period indicated.

**MITSUBISHI CEMENT CORPORATION**  
**Cushenbury plant**

**Tom Gepford**  
**Quality Control Manager**