

CERTIFICATE OF TEST

Source: Cushenbury Plant Limestone Modified Portland Cement - Block Date: 5/11/2023

ASTM designation: C 1157 – 11 for Type HE Production Period

UBC Standard: Section 21.303.1 Vol. 3 From: 04/03/2023

To: 04/19/2023

Chemical Composition:	ASTM Limits	UBC Limits	Test Results
Silicon Dioxide (SiO ₂), %			19.6
Aluminum Oxide (Al ₂ O ₃), %			5.0
Ferric Oxide (Fe ₂ O ₃), %			1.1
Calcium Oxide (CaO), %			63.9
Magnesium Oxide (MgO), %			1.7
Sulfur Trioxide (SO ₃), %			3.3
Loss on Ignition, %		7.0 Max.	5. 7
Insoluble Residue, %		1.5 Max.	1.0
Total Alkali (%Na ₂ O + 0.658 * %K ₂ O), %			0.44
Tricalcium Silicate (C3S), [b] %			47
Tricalcium Aluminate (C ₃ A), [b] %			11
CO ₂ , %			4.0
Limestone, %	15 Max.		9.9
Limestone Purity, %		85 Min.	93
Free Lime, %			1.2
PHYSICAL RESULTS:			
Blaine Fineness Average (m²/kg)			539
325 Mesh (% Passing)			99.1
Autoclave Expansion (%)	0.80 Max.		0.08
Mortar Bar Expansion (%)	0.020 Max.		0.011
Time of Set Initial Vicat (minutes)	45 / 420 Min. / I	Max	60
Air Content (% by Volume)	12 Max	22 Max.	8.2
C1702 Heat of Hydration (J/g)	(a)		415
Color (L value)	(a)		77
Compressive Strength Test:	ASTM Limits MPA psi		MPA PSI
1 Day	1	Iin.	21.2 3070
3 Day		1in.	33.2 4820
7 Day		-	37.8 5480
28 Day Mar 2023			42.5 6160

This cement has been sampled and tested in accordance with ASTM standard methods and procedures. All tests results are certified to comply with the type specification designated above. No other warranty is made or implied. We are not responsible for improper use or workmanship. The MCC laboratory is AASHTO accredited. [a] For information only. [b] Adjusted per ASTM C150 A1.6

MITSUBISHI CEMENT CORPORATION Cushenbury plant

Evan Coss

Quality Control Superintendent



CERTIFICATE OF TEST

Source: Cushenbury Plant Limestone Modified Portland Cement - Block Date: 5/11/2023

ASTM designation: C 1157 – 11 for Type HE Production Period

UBC Standard: Section 21.303.1 Vol. 3 From: 04/03/2023

To: 04/19/2023

Additional Data

Limestone Addition

% Addition:	9.9
SiO2 (%)	3.3
Al_2O_3 (%)	0.9
Fe ₂ O ₃ (%)	0.3
CaO (%)	51.6
SO ₃ (%)	0.0

Base Cement Phase Composition

C_3S	52
C_2S	20
C_3A	13
C_4AF	4

We certify that the above described data represents the material used in the cement manufactured during the production period indicated.

MITSUBISHI CEMENT CORPORATION Cushenbury plant

Evan Coss

Quality Control Superintendent